




HARDWOOD FLOORING | TECHNICAL INFORMATION



Product # 2-1177-6282



LINE | CHEVRON
COLOR | GINGER

Wood species | Oak
Grade | Rustic
Constructions | 2-layer T&G Engineered Flooring
Size | 15,0 x 127 x 548 mm (5/8" x 5" x 21 5/8")
Finish | UV-Oil

CONSTRUCTION : 2-LAYER T&G ENGINEERED FLOORING

| DIMENSIONS : | | | PACKAGING : | | |
|----------------|-------------------------|-----------|----------------|----------------------|-----------------------------|
| | | | BOX | PALLET | |
| Thickness | 15,0 mm (5/8") | | Content: | 1,392 m ² | 54 (75,168 m ²) |
| Width | 127 mm (5") | | Weight | 16 kg | 883 kg |
| Length | 548 mm (21 5/8") | | H x W x L | 168 x 275 x 681 mm | 1144 x 832 x 2050 mm |
| Average length | - | | Content: | 15 sq.ft. | 809 sq.ft. |
| Microbevel | 0,5 mm | | Weight | 35,5lb | 1954 lb |
| Joint type | tongue and groove (T&G) | H x W x L | 7" x 11" x 27" | 45" x 33" x 81" | |

DEVIATIONS :

| | | |
|------------------------|------------------------|--|
| Deviation on Thickness | ± 0,2 mm | EN 13489 ГОСТ 862.3 - 2020 ГОСТ 862.1 - 85 |
| Deviation on Width | ± 0,2 mm | |
| Height Difference | ≤ 0,2 % of width | |
| Cup | ≤ 0,2 % of plank width | EN 13489 |
| Bow | ≤ 0,1 % of length | |
| Spring | ≤ 0,5 % of length | |

CHARACTERISTICS :

| | | |
|-----------------------------|---------------------------|----------|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal penetration | 0,104 m ² ·K/W | |
| Thermal conductivity | 0,154 W/(m·K) | |
| Structural warranty | Lifetime | |

INSTALLATION :



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

STORAGE AND USAGE :



— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

FINISH : UV-OIL

| DESCRIPTION : | |
|-----------------------|---|
| Type of coating | UV-cured modified polyurethane-acrylate |
| Surface (finish) type | Semi-closed pores, wire brushed |
| Sheen | Silk matte 3 - 10 GU/60° |
| Finish warranty | - |

CLASSIFICATION SURFACE CHARACTERISTICS :

| | | |
|-------------------------------|---------------------------|----------|
| Wear resistance | Not rated | EN 438-2 |
| Scratch resistance | Not rated | EN 438-2 |
| Slip resistance | 50 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Medium | |

MAINTENANCE AND CARE CONDITIONS :

Maintenance of hardwood floors with Silk Oil finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

GRADE : RUSTIC

| DESCRIPTION : | | DESCRIPTION : | |
|------------------|--------------------------------------|----------------|--------------------------|
| Sound sapwood | No limit | Bark pocket | No limit (after filling) |
| Colour variation | No limit | Pith | Permitted |
| Knot | No limit (after filling) | Slope of grain | Permitted |
| Checks | Permitted filled up to 3 mm in width | Medullary ray | Permitted |